



MAESTRO® supreme persuades with an outstanding smoothness for an even better finish, ideal for light colour laser applications. High whiteness level and perfect opacity ensures impressive colour contrasts and trouble-free duplex printing. The smooth surface gives the paper a pleasant haptic feel commensurate with high-end applications.



Technical Data: MAESTRO® SUPREME

			60	70	80	90	100
Basis weight	g/m ²	ISO 536	60 ± 2.5	70 ± 2.5	80 ± 3.0	90 ± 3.5	100 ± 4.0
Caliper	µm	ISO 534	73 ± 3	87 ± 3	98 ± 4	106 ± 4	115 ± 4
Smoothness Bekk	sec	ISO 5627	70 ± 15	70 ± 15	70 ± 15	70 ± 15	70 ± 15
Opacity	%	ISO 2471	86.0	90.0	93.0	94.0	95.0
Brightness UV	%	ISO 2470	114.0 ± 2.0	114.0 ± 2.0	114.0 ± 2.0	5.0	5.0 ± .5
CIE Whiteness	%	ISO 11475	170 ± 4.0	170 ± 4.0	170 ± 4.0	114.0 ± 2.0	114.0 ± 2.0

			120	160	200	250	300
Basis weight	g/m ²	ISO 536	120 ± 4.5	160 ± 6.0	200 ± 6.0	250 ± 7.0	300 ± 8.0
Caliper	µm	ISO 534	135 ± 5	176 ± 6	214 ± 7	262 ± 8	315 ± 8
Smoothness Bekk	sec	ISO 5627	70 ± 15	70 ± 15	60 ± 15	60 ± 15	50 ± 15
Opacity	%	ISO 2471	96.5	99.0	99.5	99.5	99.5
Brightness UV	%	ISO 2470	5.2 ± .5	5.2 ± .5	5.5 ± .5	5.9 ± .6	5.9 ± .6
CIE Whiteness	%	ISO 11475	114.0 ± 2.0	114.0 ± 2.0	114.0 ± 2.0	114.0 ± 2.0	114.0 ± 2.0

SIGNIFICANCE OF VALUES: 2 SIGMA

Product meets EN 12281, requirements for copy paper for dry toner imaging processes and ISO 9706, requirements for permanence for paper. Production processes certified according to ISO 9001, ISO 14001 and OHSAS 18001. Standard measurement uncertainty between laboratories is not incorporated.

This specification is valid for one year after issue.